

# Testing report

## Testing description:

Tear testing according to ISO 34

## Company:

Técnica Industrial Oswaldo Filizola Ltda.


## Operator:

Tiago Ranalli

## Date:

09/04/2009 15:19:24

### Resultados do ensaio



### Parameters by testing

	Testing 1	Testing 2	Testing 3	Testing 4
<b>Thickness [ mm ]</b>	2,000	2,000	2,000	2,000
<b>Tear strength [ N/mm ]</b>	3,310	3,187	3,236	3,408

### Statistics among testings

	Average	Std Deviation	Variance	Median
<b>Thickness [ mm ]</b>	2,000	0,000	0,000	2,000
<b>Tear strength [ N/mm ]</b>	3,285	0,096	0,009	3,273

### Statistics by testing

	<b>Average</b>	<b>Std deviation</b>	<b>Variance</b>	<b>Median</b>
<b>Testing 1</b>	5,676	1,987	3,948	6,521
<b>Testing 2</b>	5,612	1,630	2,658	6,203
<b>Testing 3</b>	5,657	1,704	2,905	6,423
<b>Testing 4</b>	6,105	1,777	3,157	6,767

Remarks:

Sample manufactured on 13/02/2009 /Test piece type: Nitrile rubber 70 Shore

Remarks:

Temperature of test: 24°C

DynaView ©2005 - 2009